

AMENDMENTS TO THE ABSTRACT

Please substitute the following paragraph(s) for the abstract now appearing in the currently filed specification:

Auto body roof comprising at least one steel part and a skin part made of an aluminum alloy that is attached to the steel part before painting. The aluminum part comprises a sheet of the following composition: Si: 0.7-1.3, Fe < 0.5, Cu: 0.5-1.1, Mn: 0.4-1.0, Mg: 0.6-1.2, Zn < 0.7, Cr < 0.25, Zr+Ti < 0.20, other elements < 0.05 each and < 0.15 total, and the remainder aluminium. The aluminum part, after solution treatment, quenching and age-hardening for three weeks at room temperature, possesses a yield strength $R_{0.2}$ of less than 170 MPa, and preferably 160 MPa.